



# **SUPERFLEX<sup>®</sup>** SUGGESTED SPECIFICATION\_



## **SUPERFLEX<sup>®</sup> SHEETING**

Supply and fix 2.0mm/2.5mm thick x 1.2m wide Superflex<sup>®</sup> fully flexible vinyl sheeting, manufactured in accordance with SANS 786 and laid in FloorworX No. 62 acrylic adhesive which has been spread using a trowel fitted with an A2 notched blade at a rate of between 5.5m<sup>2</sup> and 6.5m<sup>2</sup> per litre on a previously prepared Class 1 sub-floor in accordance with SANS 10070, using FloorworX Self Leveller when required, including all cutting and waste. The sheeting must be rolled in both directions with an articulated 68kg three-sectional roller immediately after it has been laid into the adhesive. Joins must be butted, grooved and heat welded using FloorworX Welding Rod, ensuring that the welding rod bonds to more than 70% of the sheet thickness. The newly laid floor must, after 72 hours, be stripped using FloorworX Stripper, scrubbed using a diluted solution of FloorworX Rinse and then sealed with 3 coats of FloorworX Silk Matt or Gloss Sealer.

## **SUPERFLEX<sup>®</sup> TILES**

Supply and fix 2.0mm/2.5mm thick x 300mm x 300mm Superflex<sup>®</sup> fully flexible vinyl tiles, manufactured in accordance with SANS 786 and laid in FloorworX No. 62 acrylic adhesive which has been spread using a trowel fitted with an A2 notched blade at a rate of between 5.5m<sup>2</sup> and 6.5m<sup>2</sup> per litre on a previously prepared Class 1 sub-floor in accordance with SANS 10070, using FloorworX Self Leveller when required, including all cutting and waste. The flooring must be rolled in both directions with an articulated 68kg three-sectional roller immediately after it has been laid into the adhesive. The newly laid floor must, after 72 hours, be stripped using FloorworX Stripper, scrubbed using a diluted solution of FloorworX Rinse and then sealed with 3 coats of FloorworX Silk Matt or Gloss Sealer.

